



## 2K HS PRIMER

### GENERAL

CODE	DESCRIPTION
PFW10	2K HS primer white 1L
PFG10	2K HS primer grey 1L
PFB10	2K HS primer black 1L
HPF025	2K HS hardener normal 250 ml
HPF026	2K HS hardener fast 250 ml
PFW40	2K HS primer white 4L
PFG40	2K HS primer grey 4L
PFB40	2K HS primer black 4L
HPF10	2K HS hardener normal 1L
HPF10	2K HS hardener fast 1L
HPF10	2K HS hardener extra fast 1L



White



Grey



Black

### DESCRIPTION

Gerko primer filler is a two component high build acrylic primer. Provides good sandability, good filling, fast drying, sag-resistance and excellent adhesion to steel, galvanized steel and aluminium. Gerko primer filler guarantees complete all-purpose use thanks to the 3 application methods available: high build primer, primer surfacer and non sanding primer. The product is available in three colours (black, grey and white) for optimum matching of the filler colour to the topcoat.

### PROPERTIES

- Very high solids content
- Fast drying
- Easy sanding
- Reduced sanding dust
- Short refinishing times
- Can also be used wet on wet

### APPLICATION CONDITIONS

It is recommended to apply the primer at a temperature between 5 - 25°C at a humidity rate of maximum 80°C.



## 2K HS PRIMER

### MIXING RATIO

	High build primer		Primer surfacer		Non sanding	
	By volume	By weight	By volume	By weight	By volume	By weight
Primer Filler	4	100	4	100	4	100
Hardener	1	14,3	1	14,3	1	14,3
Thinner	0,5	7,15	1	14,3	2	28,6

### VISCOSITÉ



DIN 4/20°C  
18 - 25 s


**Content of volatile organic compounds**

### VOC INFORMATION

530 - 560\*

\*Ready to use mixture. VOC contents are at minimum and maximum values.

### APPLICATION



	Nozzle (mm)	Pressure (bar)
Number of layers	2 - 3	
Gravity feed spray gun HVLP	1.4 - 1.8 1.6 - 2.0	2 - 4 2 - 4
Mixture life at 20°C	1 - 2 h	
(20°C, 65% RH) Flash-off time	5 - 10 min	



## 2K HS PRIMER

### DRYING TIME

	High build primer	Primer surfacer	Non sanding
Drying time 20°C	2 - 4 h	2 - 3 h	15 - 60 min
Drying time 60°C	25 min	20 min	

### SANDING

	High build primer	Primer surfacer	Non sanding
Sanding	P320 - P400	P400 - P500	

### IR DRYING



Distance/Time depending on lamp type and power  
5 - 10 min (Guideline for IR equipment)

### SHELF LIFE

In temperatures between 15°C to 25°C under humidity of 65% the shelf life of the product is predicted to be 24 months from the date of production.

### SAFETY

See safety data sheet.

### OTHER INFORMATION

Such information is, to the best of the company's knowledge and belief, accurate and reliable as of the data indicated. However, no warranty guarantee or representation is made to its accuracy, reliability or completeness. It is the users responsibility to satisfy himself as to the suitability of such information for his own particular use.