



## AQUA MASKING TAPE

### GENERAL

CODE	DESCRIPTION
AMT19	Aqua masking tape - 19 x 50 mm
AMT24	Aqua masking tape - 24 x 50 mm
AMT30	Aqua masking tape - 30 x 50 mm
AMT38	Aqua masking tape - 38 x 50 mm
AMT50	Aqua masking tape - 50 x 50 mm



### DESCRIPTION

Aqua masking tape is a premium high temperature masking tape characterized by a waterproof crepe paper backing and a solvent borne rubber resin adhesive. Superb resistance to moisture, water and solvent base paints, and to high temperatures. Designed for wet sanding & spray painting operation in car repair application with most common paints and lacquers. Special colour backing improves visibility during the paint masking process for easy removal. Temperature resistance up to 110°C. Suitable for short – term outdoor masking operation with clean removal within 3 days. FSC® and PEFC certified masking tapes available on demand.

### FEATURES

- Medium/High adhesion
- Excellent holding power and quick stick
- Specifically designed to resist to moisture and most common water base paints
- Clean removal after drying cycle at 90°C/194°F (max. 1 hour) — 110°C/230°F (max. 30 min)
- Excellent adhesion on painted metal, rubber and glass
- Good paint anchorage
- 3 days UV resistance

### MAIN APPLICATIONS

- Professional masking for high temperature water base spray painting in Automotive refinishing industry.
- Indoor and outdoor (short-term) professional masking and painting operations



## AQUA MASKING TAPE

### TECHNICAL DATA

	Metric	Imperial Units	Test Method
Total weight	100 g/m <sup>2</sup>	100 g/m <sup>2</sup>	ISO 536
Total thickness	130 µm	5.1 mils	Internal
MD tensile strength	42 N/cm	24 Lbs/in	AFERA 5004/PSTC 131
MD elongation at break	8 %	8 %	AFERA 5004/PSTC 131
Adhesion to steel plate	2.3 N/cm	21.0 oz/in	AFERA 5001/PSTC 101
Service temperature up to (1 hour)	90°C	194°F	

### BACKING MATERIAL

Saturated crepe paper

### TYPE OF ADHESIVE

Natural rubber

### TECHNICAL INFORMATION AND PRODUCT USE

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. Gerko reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

### STORAGE AND SHELF LIFE

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of shipment. Gerko does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.